

## PGM 14 Technical Data

TenCate Bidim® PGM 14 is a mechanically bonded paving fabric made from 100% PP continuous filaments. In conjunction with a bitumen layer it acts as a barrier to the ingress of water and delays the deterioration of the pavement.

TenCate Bidim® PGM 14 is characterised by optimum bitumen storage capacity and was especially developed for new asphalt road construction, rehabilitation of older roads and conforms to EN 15381. The main functions are stress relief (STR) and sealing (B). The product is used between asphalt layers, or applied directly on concrete surfaces or cement stabilised layers.



TenCate Bidim® PGM 14

Properties	Standard	Unit	PGM 14				
Functions	EN 15381	-	STR + B				
Type of product Raw Material	- -	-	Mechanically bonded continuous filament nonwoven 100% polypropylene, UV stabilized				
Tensile strength (md/cd)	EN ISO 10319	kN/m			9		
Elongation at break	EN ISO 10319	%		100% polypropylene, UV stabilized  9 55 520 >50 1.0  12 000 140  165  1.00 1.90 3.00 3.80 150 150 150 150 285 450 570			
Grab tensile strength	ASTM D 4632	N		520			
Grab elogation	ASTM D 4632	%	>50				
Bitumen retention* *Bitumen required to saturate paving fabric only. Value does not indicate the bitumen application rate re	EN 15381 equired for construction.	kg /m²	1.0				
E-Modulus		MPa	12 000				
Mass of paving fabric	EN ISO 9864	g/m²	140				
Melting point	EN ISO 3146	°C	165				
Forms of Supply							
Width		m	1.00	1.90	3.00	3.80	
Length		m	150	150	150	150	
Area		$m^2$	150	285	450	570	
Roll weight		kg	26	46	72	92	
Rolls per pallet		-	12	12 available as single rolls			
Roll diameter		m	0.50	0.50	0.50	0.50	
Inner core diameter		m	0.12	0.12	0.12	0.12	
Recycling			100% recyclable with conventional methods				

The values given are indicative and correspond to average values obtained in our laboratories and in testing institutes. The right is reserved to make changes without notice at any time.

The rolls must be kept in dry place! Installation guidelines must be observed!

TENCATE GEOSYNTHETICS FRANCE S.A.S.

9 rue Marcel Paul – B.P. 40080 – F-95873 Bezons Cedex Fax +33 (0)1 34 23 53 48 service.fr@tencate.com www.tencategeosynthetics.com



TenCate Geosynthetics Austria Gesm.b.H, TenCate Geosynthetics France S.A.S and TenCate Geosynthetics Nethalands b.v. are certified for the design, manufacturing and sales of geotextile and geotextile related products.



